

3D PRINTING FILAMENT



designed by Eric Harrell

colorFabb _XT

*Available in 2.85mm and 1.75mm.
 $\varnothing \pm 0.05 \text{ mm}$*

processing temperature: 240C/260C
heated buildplate: 60C/70C

**Heat resistance 70C | good chemical
resistance | complies with certain FDA
food contact approvals**

ColorFabb XT is a low-odour, styrene-free 3D printing filament made with Eastman Amphora 1800 3D polymer.

You'll be able to make a lot of things that are more functional, durable, efficient, attractive and exhibit superior toughness.

